

AQUALUX STRONG

PRODUCT DESCRIPTION	Waterborne top coat based on acrylic resin for the protection and decoration of wooden surfaces with excellent covering power, with active substance for film protection against mould, yeast and algae and natural aging of wood.
PRODUCT RANGE	According to the Top Mix tinting system
THINNER	Water
GLOSS	Mat
DRYING TIME	Dry to the touch: 0,5 h/ 20°C, with 65% relative humidity and good ventilation; Completly dry: 24 h.
SOLIDS CONTENT	48-52% depending on shade
VISCOSITY	2400-2800 mPa·s (20°C), according to HRN EN ISO 2555:2008
SPREADING RATE	10-12 m ² /l in one coat, depends on application type and film thickness.
DENSITY	1,22-1,26 kg/l (HRN EN ISO 2811-1:2016)
VOC	A(d), 130 g/l; maks. 20 g/l
APPLICATION AREA	For interior and exterior use on wooden surfaces that will be subjected to a greater impact of moisture. It is used to paint new, previously painted or already treated wooden surfaces with fungicidal agents.
APPLICATION	On a dry wood (maximum wood moisture 10%) due to better absorption in the wooden structure. Old coatings should be pre-grinded with abrasive paper and well drained off all dust. On dry and clean substrates, free of rot and mold, applied by brush, spraying or roller, diluting with water if necessary. The applied coating should be protected from water in the first two days after application. Wet cleaning is possible after 2 weeks of coating applying.
OVERCOATING INTERVAL	4 h/ 20-23°C, with 65% relative humidity and good ventilation.
STORAGE	In a dry, well ventilated spaces out of direct sunlight at a temperatures between +5 °C and + 25°C.
SHELF LIFE	3 years
CERTIFICATES	For each batch of paint, corresponding certificate is being issued
NOTE	Before using, Aqualux Strong should bi mixed well. The product must not freeze!

Proizvođač zadržava pravo na eventualne kasnije izmjene. Za sve daljnje informacije obratite se našoj tehničkoj službi! Tehnički podaci se daju s namjerom da se postignu optimalni rezultati u radu s proizvodima tvrtke CHROMOS-SVJETLOST bez obveze od strane proizvođača.



CHROMOS-SVJETLOST D.O.O. :: M. STOJANOVIĆA 13 :: 35257 LUŽANI TEL. 385/35/213 800 :: FAX. 385/35/213 801 E-mail: prodaja@chromos-svjetlost.hr :: Web: www.chromos-svjetlost.hr